



PIEL/LEATHER/CUIR

Ficha técnica / Technical data sheet / Fiche technique

Composición 100% Piel Bovina	Composition 100% Bovine Leather	Composition 100% Cuir de veau
Curtición Al cromo	Tannerie By chrome	Tannage Au chrome
Tintada Pasante	Tannerie By Passes	Teinté Stagiaire
Acabado Pigmentado	Finish Pigmented	Fini pigmenté
Grabado Madras	Engrave Madras	Graveur Madras
Tintada Pasante	Tannerie By Passes	Teinté Stagiaire
Talla media ca. 4 m2. Aprox.	Medium size ca. 4 m2. Aprox.	Taille moyenne ca. 4 m2. Aprox.
Espesor medio ca. 0.9 – 1 mm.	Average thickness ca. 0.9 – 1 mm.	Épaisseur moyenne ca. 0.9 – 1 mm.
Flexometría 20.000 iuf/20	Flexometry 20.000 iuf/20	Flexometrie 20.000 iuf/20
Solidez al frote En seco: 500 iuf 450 En húmedo: 100 iuf 450	Fastness to Rubbing Dry: 500 iuf 450 Wet: 100 iuf 450	Solidité aux frottements Sec: 500 iuf 450 Mouillé: 100 iuf 450
Valor pH min. 3,5 din 53312	Valor pH min. 3,5 din 53312	Valor pH min. 3,5 din 53312



No usar lejía
Do not use bleach
Ne pas utiliser eau javel



Lavar con paño húmedo
Wash with damp cloth
Laver avec un chiffon
humide



Evitar secar al sol
Avoid drying in the sun
Éviter sécher au soleil



Libre de CFC
CFC free
Sans CFC



Libre de pentaclorofenol
Pentachlorophenol Free
Pas pentachlorophénol